



High-Performance Spray Foam Insulation for Homes and Commercial Buildings.

SPRAY 6" rin ONE PASS R-Value R-7.2 @ 1" Adds structural integrity 1.7 lb. Density

The US Department of Energy states that 40% of air loss is due to air infiltration.

With continuous research and development, **ThermoSeal** continues to lead the spray foam insulation industry in both quality and diversity of spray foam products. Our products insulation performance is the clear winner in energy savings, sound control, moisture vapor permeance, lifespan, and cellular structure, therefore reducing waste and cost at the same time.







- Sales Support
- Tech Support
- Co-op Marketing
- Leads
- Competitive Pricing & Terms
- Training

TECHNICAL DATA SHEET

Material Specification Criteria | Project Submittal Data



Thermoseal ONE

Medium Density • Closed Cell Spray Foam Insulation



ThermoSeal ONE is a two component, semi-rigid, medium density, 1.7 lb closed cell polyurethane foam insulation system which simultaneously insulates and air-seals your building structure. Thermoseal ONE requires the use of an "A" component (ISO) and a blended "B" component (RESIN), which contains ZERO ozone depleting catalysts, polyols and fire retarding materials. ThermoSeal ONE is designed to make homes more energy efficient, quieter, healthier and more comfortable. ThermoSeal ONE is applied as a liquid spray which expands approximately 15 times its initial mass and cures within seconds into a semi-rigid mass. ThermoSeal ONE fills all building cavities completely sealing all cracks, crevices, and voids where air loss and infiltration are most common.

Physical Properties			
Property	Value	Test Method	
R-Value	7.2 @ 1"	ASTM C 518	
Core Density	1.7 LB / Cubic Foot	ASTM D 1622	
Closed Cell Content	>= 92%	ASTM D 2586	
Water Vapor Transmission - Permeance	Perms: .8 @ 1" / .23 @ 3.5"	ASTM E 96	
Air Leakage Rate	Zero (0) ft3/s.ft2 @ 75Pa	ASTM E 283	
Compressive Strength (PSI)	20	ASTM D 1621	
Tensile Strength (PSI)	60	ASTM D 1623	
Dimensional Stability	< 5%	ASTM D 2126	
Fungi Resistance	Zero Rating	ASTM G 21	
Fire Properties			
Property	Value	Test Method	
Surface Burning Charateristics • Flame Spread • Smoke Index	Class 1 Pass <25 <450	ASTM E 84	
Ignition Barrier	Complies with the applicable requirements of ICC-ES AC377 Appendix X for use in attics and crawlspaces without a prescriptive implies parrier.	ICC- ES AC377 Appendix X	

Flame Spread Smoke Index	<25 <450		
Ignition Barrier	Complies with the applicable requirements of ICC-ES AC377 Appendix X for use in attics and crawlspaces without a prescriptive ignition barrier. ICC- ES AC377 Appendix X		
Thermal Barrier	Pass using DC315 manufactured by International Fireproof Technology, Inc at (88.88 sq. ft./gal @ 18 mils wet and 12 mils dry) coverage rate of 1.136 gallons (4.3 L) per 100 square feet (9.3 m2)		
Evaluation Report			
F 1 11 B 1			

Evaluation Report	IAPMO ER-0602	IAPMO ES
Wind Uplift Test	PASS @135 (psf) / 233 (mph)	UL 1897

Thermoseal, Ilc Po Box 32 New Canaan, CT. 06840

TDS V2.2 September 04, 2018

www.ThermoSealUSA.com 800.853.1577 info@ThermosealUSA.com



ThermoSeal Closed Cell Spray Foam creates an Air Barrier, Vapor



ThermoSeal One